

Hangzhou Easy Electric Wire and Cable Co.,LTD


Add: Room 305, Building 2, No. 380 Fengxin Road Hangzhou, China

www.eescable.com

TEST REPORT

Products	ACSR Sparrow Size		1×2.67+6×2.67				
Standard	ASTM B232 -01	Invoice No.	20220714001	Date	2022.07.14		
NO.	Item	Standards and	Requirements	Test Results	Evaluation		
1	Structure						
1-1	Number Of AL Wire	6		6	Qualified		
1-2	Number Of Steel Wire	1		1	Qualified		
1-3	Diameter Of Conductor	8.01		8.02	Qualified		
1-4	20℃ Max D.C Resistance	≤0.85406		0.8497	Qualified		
2	Surface Of Conductor						
2-1		The Surface Sha Stranded Compac Broken, Jumpin Strands.	ctly, No Missing,	Smooth, Compact	Qualified		
3	Structure Performance						
3-1	Outer Stranding Direction Of Conductor	Rightward		Rightward	Qualified		
3-2	Lay Ratio Of Conductor	10-14		13.5	Qualified		
4	Aluminum Wire Properties						
4-1	Diameter Of AL Wire	2.67	±0.03	2.68/2.67/2.67	Qualified		
4-2	Min. Tensile Strength	185N/	mm2	$192\mathrm{N/mm2}$	Qualified		
4-3	Wrapping Test	The wire shall around 8 times of the wire, helix 6 turns, cra	the diameter from a close wire shall not	Not crack	Qualified		
5	Steel Wire Properties						
5-1	Diameter Of Steel Wire	2.67(-0.05,+0.05)		2.67	Qualified		
5-2	Min. Tensile Strength	1410N		1440N/mm2	Qualified		

Add: Room 305, Building 2, No. 380 Fengxin Road, Hangzhou, China



Hangzhou Easy Electric Wire and Cable Co.,LTD

Add: Room 305, Building 2, No. 380 Fengxin Road Hangzhou, China

www.eescable.com

5-3	Mass of Zinc Coating	≥244 g/mm2	251 g/mm2	Qualified
5-4	Elongation(250mm)	≥3.5%	4.1%	Qualified

Tested by: Shaoqiong He

Checked by: Guohui Xu

杭州益睿电线电缆有限公司 BANGZHOU EASY ELECTRIC VIRE AND CABLE CO., LTD.